



PSI™ STEEL FIBER CUH8060

STEEL MACROFIBER - PREMIUM ULTRA HIGH

EUCLID CHEMICAL

PRODUCT INFORMATION

PACKAGING

- 20kg(44lb) Paper Bag

SPECIFICATIONS/COMPLIANCES

- ASTM A 820/A820M
- ASTM C1116/C1116M
- EN 14889-1

TECHNICAL INFORMATION

Deformation: Hooked-end

Length: 60 mm (2.36 inch)

Diameter: 0.75 mm (0.029 inch)

Aspect ratio(l/d): 80

Quantity of fibers: 2624 fibers/kg
(1,190 fibers/lb.)

Tensile strength (R_m): 1,800 MPa
(261,000 psi)

Young's Modulus: 210,000 N/mm²
(30,457,900 psi)

DESCRIPTION

PSI Steel Fiber CUH8060 is steel fiber used cold-drawn wire for reinforced concrete. PSI Steel Fiber CUH8060 is designed in order to avoid balling problem in concrete and to improve the durability of concrete. PSI Steel Fiber CUH8060 can replace all conventional reinforce methods for concrete or can be used to combine with them.

PRODUCT CHARACTERISTICS

FEATURES & BENEFITS

- increase load bearing capacity.
- control shrinkage cracks
- Improve durability.
- Reinforce the concrete multidirectionally
- reduce construction time

PRIMARY APPLICATIONS

- Industrial Slab and Floor
- Commercial Floor
- Cast in Place Concrete
- Precast Concrete Product

AVAILABILITY

- Contact your local Stoncor Middle East LLC representatives.

STORAGE & HANDLING

- Store in dry area
- Wear gloves when handling fibre

CLEAN UP

- Loose fiber material should be disposed in proper receptacles for refuse. Finishing equipment with fibers embedded in concrete should be thoroughly cleaned.



To the best of our knowledge the technical data contained herein are true and accurate at the date of issuance and are subject to change without prior notice. User must contact StonCor Middle East to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to StonCor Middle East Quality Control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. Prices and cost data, if shown, are subject to change without prior notice. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY STONCOR MIDDLE EAST, EXPRESS OR IMPLIED, STATUTORY BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE
(June 2023)
CUH8060

PSI™ STEEL FIBER

StonCor Middle East LLC
Tel: +971 (0) 4 2579033
E-mail: info@stoncor-me.com

www.stoncor-me.com